

Producteur : EQIOM - Carrière de ROUVRES

Granulats : Mélange 0/14rec.

Petrographie : Calcaire

Elaboration : Recomposé

L'essai LA est réalisé sur la fraction 10/14.

Résultats de production

	du 13/02/25 au 04/06/25																
	0.063	0.08	0.125	0.25	0.5	1	2	4	5	6.3	10	12.5	14	20	28	40	MB
Maximum	3.00	3.84	5.80	10.94	17.08	30.49	43.53	58.91	67.58	76.15	89.63	95.00	97.40	100.00	100.00	100.00	0.50
Xf+1.25xEcart-types	3.12	3.83	5.78	10.77	17.05	30.18	43.35	58.65	67.17	75.49	89.50	94.83	97.47	100.00	100.00	100.00	0.50
Moyenne Xf	2.08	2.72	4.48	8.88	15.92	27.44	40.98	56.71	63.65	70.47	86.66	93.53	97.19	100.00	100.00	100.00	0.50
Xf-1.25xEcart-types	1.05	1.62	3.18	7.00	14.79	24.70	38.60	54.77	60.13	65.44	83.81	92.23	96.91	100.00	100.00	100.00	0.50
Minimum	0.99	1.67	3.26	7.37	14.88	25.44	38.98	55.59	61.15	67.50	84.09	92.74	96.88	100.00	100.00	100.00	0.50
Ecart-type	0.830	0.887	1.041	1.508	0.900	2.189	1.899	1.553	2.813	4.020	2.279	1.041	0.223	0.000	0.000	0.000	0.000
Nombre de résultats	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3	3
Dernier	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025	04/06/2025

